

# Wieland-B09/B10

CuSn8 | Phosphor bronze

## Material designation

EN	CuSn8 CW453K
UNS	C52100

## Chemical composition\*

Cu	balance
Sn	8 %
P	0.01–0.4 %

\*Reference values in % by weight

## Physical properties\*

Electrical conductivity	MS/m %IACS	6.5 11
Thermal conductivity	W/(m·K)	58
Thermal expansion coefficient (0–300 °C)	10 <sup>-6</sup> /K	18.5
Density	g/cm <sup>3</sup>	8.8
Modulus of elasticity	GPa	115

\*Reference values at room temperature

## Corrosion resistance

In general excellent resistance to corrosion in seawater, industrial atmosphere and to stress corrosion cracking.

## Product standards

Rod	EN 12163
Wire	EN 12166
Section	EN 12167
Tube	EN 12449

## Material properties and typical applications

Wieland-B09/B10 is a phosphor bronze with a tin content of 8 % making it possible to achieve very high mechanical strength and good spring properties. It has excellent wear and corrosion resistance and is therefore also used for bearings. Phosphor bronzes exhibit good cold working properties and can be satisfactorily machined with adequate tooling parameters.

A very pure type of CuSn8 is **Wieland-B10** meeting the highest demands, for example, of Bourdon tubes.

## Types of delivery

The BU Extruded Products supplies bars, wire, sections and tubes. Please get in touch with your contact person regarding the available delivery forms, dimensions and tempers.

## Fabrication properties

### Forming

Machinability (CuZn39Pb3 = 100 %)	25 %
Capacity for being cold worked	excellent
Capacity for being hot worked	poor

### Joining

Resistance welding (butt weld)	fair
Inert gas shielded arc welding	excellent
Gas welding	good
Hard soldering	good
Soft soldering	excellent

### Surface treatment

Polishing	
mechanical electrolytic	good fair
Electroplating	good

### Heat treatment

Melting range	960–1,020 °C
Hot working	700–800 °C
Soft annealing	500–700 °C 1–3 h
Thermal stress relieving	200–300 °C 1–3 h

# Wieland-B09/B10

CuSn8 | Phosphor bronze

## Mechanical properties according to EN

Round rods/polygonal rods													acc. to EN 12163	
Temper	Diameter		Width across flats		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm		mm		MPa	MPa		A100	A11.3	A	HB			
	from	to	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		all		as manufactured – without specified mechanical properties									
R390	2	60	2	60	390	–	280	35	40	45	–	–		
H085	2	60	2	60	–	–	–	–	–	–	85	125		
R450	2	50	2	50	450	280	–	18	22	26	–	–		
H135	2	50	2	50	–	–	–	–	–	–	135	165		
R550	2	12	2	12	550	400	–	10	12	15	–	–		
H160	2	12	2	12	–	–	–	–	–	–	160	190		
R620	2	8	–	–	320	500	–	5	8	–	–	–		
H180	2	8	–	–	–	–	–	–	–	–	180	–		
R750	2	4	–	–	750	680	–	–	–	–	–	–		
H210	2	4	–	–	–	–	–	–	–	–	210	–		

Rectangular rods											acc. to EN 12167	
Temper	Thickness		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Hardness			
	mm		MPa	MPa		A100	A11.3	A	HB			
	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		as manufactured – without specified mechanical properties									
R390	3	50	390	–	280	35	40	45	–	–		
H085	3	50	–	–	–	–	–	–	85	125		
R450	3	6	450	280	–	18	22	–	–	–		
H135	3	6	–	–	–	–	–	–	135	165		
R550	3	6	550	400	–	10	12	–	–	–		
H160	3	6	–	–	–	–	–	–	160	190		

Tubes										acc. to EN 12449	
Temper	Wall thickness	Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %	Hardness					
	mm	MPa	MPa		A100	HV		HB			
	max.	min.	min.	max.	min.	min.	max.	min.	max.		
M	20	as manufactured – without specified mechanical properties									
R380	10	380	–	290	55	–	–	–	–		
H080	10	–	–	–	–	80	110	75	105		
R450	5	450	250	–	25	–	–	–	–		
H115	5	–	–	–	–	115	160	110	155		
R520	3	520	440	–	10	–	–	–	–		
H155	3	–	–	–	–	155	190	150	185		
R590	2	590	520	–	5	–	–	–	–		
H180	2	–	–	–	–	180	–	175	–		

Round wires											acc. to EN 12166	
Temper	Diameter		Tensile strength R <sub>m</sub>	Yield strength R <sub>p0.2</sub>		Elongation %			Härte			
	mm		MPa	MPa		A100	A11.3	A	HB			
	from	to	min.	min.	max.	min.	min.	min.	min.	max.		
M	all		as manufactured – without specified mechanical properties									
R390	0.1	12	390	–	280	35	40	45	–	–		
H090	1.5	12	–	–	–	–	–	–	90	130		
R450	0.1	12	450	280	–	18	22	26	–	–		
H140	1.5	12	–	–	–	–	–	–	140	170		
R550	0.1	12	550	400	–	10	12	15	–	–		
H170	1.5	12	–	–	–	–	–	–	170	200		
R620	0.1	8	620	500	–	4	6	–	–	–		
H185	1.5	8	–	–	–	–	–	–	185	–		
R750	0.1	4	750	680	–	–	–	–	–	–		
H220	1.5	4	–	–	–	–	–	–	220	–		
R920	0.1	1.5	920	800	–	–	–	–	–	–		
H265	–	1.5	–	–	–	–	–	–	265	–		

Wieland-Werke AG | Graf-Arco-Straße 36 | 89079 Ulm | Germany  
 info@wieland.com | wieland.com

This printed matter is not subject to revision. No claims can be derived from it unless there is evidence of intent or gross negligence. The product characteristics are not guaranteed and do not replace our experts' advice.